

STAND UP POUCHES

<i>Properties</i>	<i>Unit</i>	<i>Data</i>	<i>Test method</i>
<i>Thickness</i>	µm	12/100	DIN 53370
Permeability			
<i>Water vapour</i>	g/m ² d	<2	DIN 53122 23°C/85%RH
<i>Oxygen (O₂)</i>	cm ³ /m ² dbar	<120	DIN 53380 23°C/75%RH
<i>Carbon dioxid (CO₂)</i>	cm ³ /m ² dbar	<610	DIN 53380 23°C/75%RH
<i>Nitrogen (N²)</i>	cm ³ /m ² dbar	<50	DIN 53380 23°C/75%RH
Mechanical Strength			
<i>Tensile strength MD</i>	N/15mm		DIN 53455 23°C/50%RH
<i>Tensile strength TD</i>	N/15mm		DIN 53455 23°C/50%RH
<i>Sealing Temperature</i>	°C	120-150	
<i>Temperature Consistency</i>	°C	100	